



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 18/2 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	9.06	S'	
	CV%	0.68	%	
Yarn Twist	TPI	9.83	T/inch	
	TPM	387.01	T/m	
Yarn Evenness	Uster U%	6.19	%	
	Thin Places	0	/ km	
	Thick Places	3.3	/ km	
	Neps	5	/ km	
Yarn Hairiness	H	10.81	%	
	CV _b	2.20	%	
Yarn Strength	Elongation	average%	12.40	%
		CV%	3.20	%
	Lea Tensile Strength	-	kg/120yd	
	Single Yarn Tensile Strength	2,398	gm	
	RKM	36.78	gm/tex	
Package Length		27,300	m	

Remark

UNWAXED