



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 18/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	18	S'	
	CV%	0.95	%	
Yarn Twist	TPI	13.14	T/inch	
	TPM	517.32	T/m	
Yarn Evenness	Uster U%	7.81	%	
	Thin Places	0	/ km	
	Thick Places	3.8	/ km	
	Neps	5	/ km	
Yarn Hairiness	H	7.46	%	
	CV _b	1.50	%	
Yarn Strength	Elongation	average%	12.29	%
		CV%	4.49	%
	Lea Tensile Strength	152	kg/120yd	
	Single Yarn Tensile Strength	1,134	gm	
	RKM	34.56	gm/tex	
Package Length		63,600	m	

Remark WAXED



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 18/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count		17.95	S'
	CV%		0.95	%
Yarn Twist	TPI		12.21	T/inch
	TPM		480.71	T/m
Yarn Evenness	Uster U%		8.03	%
	Thin Places		0	/ km
	Thick Places		11.7	/ km
	Neps		12.1	/ km
Yarn Hairiness	H		8.49	%
	CV _b		3.20	%
Yarn Strength	Elongation	average%	11.96	%
		CV%	5.05	%
	Lea Tensile Strength		148	kg/120yd
	Single Yarn Tensile Strength		1,173	gm
	RKM		35.64	gm/tex
Package Length			63,000	m

Remark UNWAXED