



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 20/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count		19.99	S'
	CV%		1.49	%
Yarn Twist	TPI		12.66	T/inch
	TPM		498.42	T/m
Yarn Evenness	Uster U%		8.09	%
	Thin Places		0	/ km
	Thick Places		7.9	/ km
	Neps		8.3	/ km
Yarn Hairiness	H		7.46	%
	CV _b		2.90	%
Yarn Strength	Elongation	average%	12.17	%
		CV%	3.87	%
	Lea Tensile Strength		136	kg/120yd
	Single Yarn Tensile Strength		1,014	gm
	RKM		34.31	gm/tex
Package Length			74,000	m

Remark WAXED