



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 30/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	29.7	S'	
	CV%	1.04	%	
Yarn Twist	TPI	15.27	T/inch	
	TPM	601.18	T/m	
Yarn Evenness	Uster U%	9.01	%	
	Thin Places	0.4	/ km	
	Thick Places	5.8	/ km	
	Neps	10.8	/ km	
Yarn Hairiness	H	6.27	%	
	CV _b	1.60	%	
Yarn Strength	Elongation	average%	10.37	%
		CV%	5.74	%
	Lea Tensile Strength	80	kg/120yd	
	Single Yarn Tensile Strength	623	gm	
	RKM	31.32	gm/tex	
Package Length		111,600	m	

Remark WAXED