



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 34/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count		33.99	S'
	CV%		1.14	%
Yarn Twist	TPI		16.48	T/inch
	TPM		648.82	T/m
Yarn Evenness	Uster U%		9.61	%
	Thin Places		1.3	/ km
	Thick Places		7.9	/ km
	Neps		17.1	/ km
Yarn Hairiness	H		6.16	%
	CV _b		2.40	%
Yarn Strength	Elongation	average%	10.47	%
		CV%	4.47	%
	Lea Tensile Strength		70	kg/120yd
	Single Yarn Tensile Strength		552	gm
	RKM		31.79	gm/tex
Package Length			126,000	m

Remark WAXED