



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 36/2 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	18.52	S'	
	CV%	0.74	%	
Yarn Twist	TPI	14.02	T/inch	
	TPM	551.97	T/m	
Yarn Evenness	Uster U%	7.15	%	
	Thin Places	0	/ km	
	Thick Places	3.8	/ km	
	Neps	6.7	/ km	
Yarn Hairiness	H	8.59	%	
	CV _b	2.10	%	
Yarn Strength	Elongation	average%	11.00	%
		CV%	5.87	%
	Lea Tensile Strength	139	kg/120yd	
	Single Yarn Tensile Strength	1,071	gm	
	RKM	33.59	gm/tex	
Package Length		54,500	m	

Remark

UNWAXED