

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 40/2 POLYESTER 100% LOT 2031N3**

Yarn Count	Actual count		19.92	S'
	CV%		0.61	%
Yarn Twist	TPI		16.31	T/inch
	TPM		642.12	T/m
Yarn Evenness	Uster U%		7.34	%
	Thin Places		0	/ km
	Thick Places		2.1	/ km
	Neps		3.3	/ km
Yarn Hairiness	H		7.51	%
	CV _b		1.40	%
Yarn Strength	Elongation	average%	10.69	%
		CV%	6.64	%
	Lea Tensile Strength		139	kg/120yd
	Single Yarn Tensile Strength		1,007	gm
	RKM		33.95	gm/tex
Package Length			63,300	m

Remark

UNWAXED