



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/2 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	20.38	S'	
	CV%	0.49	%	
Yarn Twist	TPI	16.31	T/inch	
	TPM	642.12	T/m	
Yarn Evenness	Uster U%	7.47	%	
	Thin Places	0	/ km	
	Thick Places	1.7	/ km	
	Neps	2.9	/ km	
Yarn Hairiness	H	7.46	%	
	CV _b	0.80	%	
Yarn Strength	Elongation	average%	12.30	%
		CV%	5.76	%
	Lea Tensile Strength	129	kg/120yd	
	Single Yarn Tensile Strength	1,034	gm	
	RKM	35.67	gm/tex	
Package Length		59,600	m	

Remark

UNWAXED