



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count		40.03	S'
	CV%		0.97	%
Yarn Twist	TPI		20.36	T/inch
	TPM		801.57	T/m
Yarn Evenness	Uster U%		10.15	%
	Thin Places		2.9	/ km
	Thick Places		10.8	/ km
	Neps		19.6	/ km
Yarn Hairiness	H		5.34	%
	CV _b		1.70	%
Yarn Strength	Elongation	average%	10.23	%
		CV%	6.77	%
	Lea Tensile Strength		54	kg/120yd
	Single Yarn Tensile Strength		455	gm
	RKM		30.81	gm/tex
Package Length			147,400	m

Remark WAXED



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road,KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 40/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count		40.19	S'
	CV%		1.88	%
Yarn Twist	TPI		20.36	T/inch
	TPM		801.57	T/m
Yarn Evenness	Uster U%		10.40	%
	Thin Places		4.6	/ km
	Thick Places		11.7	/ km
	Neps		24.2	/ km
Yarn Hairiness	H		5.63	%
	CV _b		3.20	%
Yarn Strength	Elongation	average%	10.58	%
		CV%	4.80	%
	Lea Tensile Strength		56	kg/120yd
	Single Yarn Tensile Strength		445	gm
	RKM		30.30	gm/tex
Package Length			137,800	m

Remark UNWAXED