



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 45/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	44.8	S'	
	CV%	1.56	%	
Yarn Twist	TPI	20.36	T/inch	
	TPM	801.57	T/m	
Yarn Evenness	Uster U%	10.81	%	
	Thin Places	10.4	/ km	
	Thick Places	21.7	/ km	
	Neps	27.5	/ km	
Yarn Hairiness	H	5.37	%	
	CV <sub>b</sub>	4.00	%	
Yarn Strength	Elongation	average%	9.87	%
		CV%	5.66	%
	Lea Tensile Strength	49	kg/120yd	
	Single Yarn Tensile Strength	385	gm	
	RKM	29.19	gm/tex	
Package Length		166,000	m	

Remark WAXED