



## CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,  
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand  
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532  
<http://www.chiempatana.com>  
 E-mail:info@chiempatana.com

### SPECIFICATION

#### NE 50/2 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	25.23	S'	
	CV%	0.68	%	
Yarn Twist	TPI	17.88	T/inch	
	TPM	703.94	T/m	
Yarn Evenness	Uster U%	8.09	%	
	Thin Places	0	/ km	
	Thick Places	3.3	/ km	
	Neps	4.2	/ km	
Yarn Hairiness	H	7.14	%	
	CV <sub>b</sub>	2.80	%	
Yarn Strength	Elongation	average%	11.15	%
		CV%	3.44	%
	Lea Tensile Strength	98	kg/120yd	
	Single Yarn Tensile Strength	734	gm	
	RKM	31.34	gm/tex	
Package Length		80,000	m	

Remark

UNWAXED