



CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4,322447-8 Fax.(66-34)322559,225532
<http://www.chiempatana.com>
 E-mail:info@chiempatana.com

SPECIFICATION

NE 50/1 POLYESTER 100% LOT 2030P

Yarn Count	Actual count	49.67	S'	
	CV%	1.21	%	
Yarn Twist	TPI	22.57	T/inch	
	TPM	888.58	T/m	
Yarn Evenness	Uster U%	10.87	%	
	Thin Places	6.3	/ km	
	Thick Places	20	/ km	
	Neps	24.6	/ km	
Yarn Hairiness	H	4.86	%	
	CV _b	1.60	%	
Yarn Strength	Elongation	average%	9.48	%
		CV%	5.66	%
	Lea Tensile Strength	42	kg/120yd	
	Single Yarn Tensile Strength	360	gm	
	RKM	30.24	gm/tex	
Package Length		174,200	m	

Remark WAXED