

CHIEM PATANA TEXTILES CO.,LTD.

23/3 Moo 3. Tambon Yaicha,
 Petkaseam Road, KM 33 Nakhornpathom, 73110 Thailand
 Tel. (66-34)311273-4, 322447-8 Fax. (66-34)322559, 225532
<http://www.chiempatana.com>
 E-mail: info@chiempatana.com

SPECIFICATION**NE 60/1 POLYESTER 100% LOT 2012M2**

Yarn Count	Actual count		60.23	S'
	CV%		0.53	%
Yarn Twist	TPI		27.32	T/inch
	TPM		1075.59	T/m
Yarn Evenness	Uster U%		11.70	%
	Thin Places		27.1	/ km
	Thick Places		32.5	/ km
	Neps		50	/ km
Yarn Hairiness	H		4.73	%
	CV _b		3.90	%
Yarn Strength	Elongation	average%	8.85	%
		CV%	7.41	%
	Lea Tensile Strength		33	kg/120yd
	Single Yarn Tensile Strength		292	gm
	RKM		29.82	gm/tex
Package Length			182,000	m

Remark UNWAXED